


# LAMIECCO WOOD REPORT ABRASION



**Lamiecco**  
ecological coverings



LAMIECCO TECHNOLOGICAL CENTER - CTL  
Rua Souza Lobo, 625  
CEP 99255-000 - MONTAURI- RS - BRAZIL  
PHONE: 54 3319 1218

## TECHNICAL INFORMATION CTL 013 / 2016- CLI

### 1. INTRODUCTION

Lamiecco Technological Center - CTL, has performed the test on the material abrasion LAMIECCO WOODS.

### 2. MATERIAL DESCRIPTION

The analyzed material receives paint finish as standard.

### 3. TEST PROCEDURE EMPLOYEE

The test was perform based on the ABNT NBR 15761: Furniture of wood: Requirements and test methods for decorative laminates, wetermining that the material should be subjected to 100 cycles abrasímetro waber, and should lose only 8.5 mg of mass at the end of cycle determined. (0,085mg / cycle).

### 4. TEST RESULTS

The sample was tested on these parameters, and the test end mass. It was measured in an analytical balance with three decimal places of precision (0,000g) detected loss of 0.01mg / cycle, state thus 88.2% higher than required by the standard. (See ANNEX, Figure 01)

### 5. CONCLUSION

The material is suitable for covering purposes, and rated above the norm.

## ANNEX



IMAGE 01: ABRASION TEST

Responsible Signature:

*Flavia S. De Marco*

Name: Flavia Schenato de Marco  
Responsible for Lamiocco Technology Center  
Date: 06/04/2016, Montauri, RS